



olivier.sandre@u-bordeaux.fr

@olive_free



MAGNETIC NANOPARTICLES: SYNTHESIS, PROPERTIES AND BIOMEDICAL APPLICATIONS

Olivier Sandre, senior CNRS researcher at Univ. Bordeaux, France




ugr | Universidad
de Granada

Magnetic nanoparticles (MNPs) Part 2: Biological applications

- Introduction: why combining polymers and magnetic nanoparticles?
- Magnetic polymer vesicles: tumor homing, MRI and magnetic drug-delivery
- Magnetic polymer micelles: magnetic cyto-toxicity and the puzzle of “cold hyperthermia” → Need of analysis method at sub-cellular scales (μm , $\text{nm}\dots$)
- Magnetic hyperthermia to induce bio-luminescence \leftrightarrow thermal dose
- Grafting of thermosensitive polymers onto iron oxide: synthetic or “biomimetic” polymers (recombinant elastin-like peptides)
- Use to probe temperature by the MRI (positive) contrast


- Basic principles of Magnetic Resonance Imaging
- Proton relaxing properties of individual nanoparticles (USPIOs)
- Proton relaxing properties of MNPs clustered by polymer chains (SPIOs) : Applications for magnetic guiding and MRI contrast enhancement
- Relaxivity of more complex shapes: rodlike (magnetic ‘nanoworms’, magnetic nanogels, magnetic micelles or vesicles (polymersomes)...



- NMR : Purcell et Bloch (1946)
- First NMR Images using gradients: Lauterbur & Mansfield (1973)
- First Human Head (1979)
- Nobel Prize in Medicine (2003): Lauterbur & Mansfield

“Negative” Contrast Agents

Microscopic outer sphere theory



Diffusion of water molecules around magnetic particles

$$\frac{1}{T_{1,2}} = \frac{1}{T_{1,2}^{\text{int}}} + R_{1,2}[\text{Conc.}]$$

T_1 : longitudinal relax. time

T_2 : transverse relax. time

$R_{1,2}$: relaxivity

(Gillis, Koenig,
Magn. Res. Med. 1987)


MRI enables to see inside your brain!




Magnetic Resonance Imaging

MRI images originate from differences in relaxation times of protons in tissues
Contrast depends on the RF pulses sequence (T_2 vs T_1 -weighting)

T_2^* -weighted
 $T_E > 120\text{ms}$, $T_R > 2.5\text{s}$



T_1 -weighted
 $T_E < 20\text{ms}$, $T_R < 600\text{ms}$




Hiwatashi A et al. Am J Roentgenol 2003; **181**: 1705–1709.

Magnetic NPs as MRI positive/negative contrast agents

University of MONS (Belgium) molecular NMR and biophysics labs

Y. Gossuin et al., *WIRE Nanomed Nanobiotech.* **2008**, 1, 299; S. Laurent et al. *Chem. Rev.* **2008**, 108, 2064




MRI based on the spin-echo sequence:

$$S_{\text{MRI}} \propto \rho_{\text{H}} \left(1 - e^{-TR/T_1}\right) \cdot e^{-TE/T_2}$$

T_1 -weighted: $TR=100$ ms $TE=2.8$ ms flip angle = 70°

T_2 -weighted: $TR=300$ ms $TE=12$ ms

“Outer Sphere” model:




$$R_2 = \frac{1}{T_2} = \left(\frac{1}{T_2} \right)_0 \times (1 + r_2 \cdot [\text{Fe}])$$

$\text{s}^{-1} \cdot \text{mM}_{\text{Fe}}^{-1}$


→ relaxometric experiments to predict MRI contrast

Signal in MRI: recall of NMR basics




- Applied B_1 radio frequency pulse at ω_0
- Energy supply creates excitation which flips M_z from the z -axis towards the xy -plane

T_1 relaxation



T_1 (spin-lattice) relaxation time = measure of the time required to regain longitudinal magnetization


T_2 relaxation



T_2 (spin-spin) relaxation time = measure of the time required to regain decoherence of the transverse nuclear spin magnetization

HA Sharma, Acta Neuropsychiatrica 2009; 21:200-201

Simplest MRI sequence: spin-echo




$$I = M_0 \left[1 - \exp \left(-\frac{TR}{T_1} \right) \right] \exp \left(-\frac{TE}{T_2} \right)$$

T_1 -weighted image → short TR (typically < 500ms)

T_2 -weighted image → long TE (typically > 60ms)

(U)SPIOs as MRI contrast agents

“Outer Sphere” model:




$$R_2 = \frac{16}{45} \tau_D f (\Delta\omega)^2$$

$$\Delta\omega\tau_D < 1$$

$$\Delta\omega = \frac{\gamma \mu_0 M_v}{3}$$

Signal for a spin-echo sequence:

$$S_{\text{MRI}} \propto \rho_{\text{H}} \left(1 - e^{-TR/T_1}\right) \cdot e^{-TE/T_2}$$



$$R_2 = \frac{1}{T_2} = \left(\frac{1}{T_2} \right)_0 \times (1 + r_2 \cdot [\text{Fe}])$$


$\text{s}^{-1} \cdot \text{mM}_{\text{Fe}}^{-1}$

→ relaxometric experiments to predict MRI contrast


Y. Gossuin, P. Gillis, A. Hocq, Q. L Vuong, A. Roch (**U Mons, Belgium**) *WIRE Nanomed. Nanobiotech.* 2008, 1, 299

T_2 relaxivity as a function of magnetic core size for USPIOs

Collaboration with Lam Vuong & Yves Gossuin, Mons, Belgium





Can one predict T_2 relaxivity of clustered USPIOs (SPIOs)?




Scaling laws vs. exact laws...

- Analytic solutions of equations in Physics or phenomenological (empirical) laws in engineering sciences → very precise but only in their validity range



Isaac NEWTON (1687),
*Philosophiae Naturalis
Principia Mathematica*

- Numerous examples of scaling law in polymer science, eg. lamellar period for diblock copolymers → approximate but predictive over a wide range



Pierre-Gilles de GENNES (1979)
Scaling concepts in polymer physics

Correct normalization of relaxometric data

in the “Motional Averaging Regime”

$$R_2 = \frac{16}{45} \tau_D f (\Delta\omega)^2 \quad [\Delta\omega\tau_D < 1]$$

$$\tau_D = \frac{d^2}{4D}$$

$$\Delta\omega = \frac{\gamma\mu_0 M_v}{3}$$

volume fraction (no unit)


$$\frac{f}{[\text{Fe}]} = v_{\text{mat}} = \frac{M_{\text{MO}\cdot\text{Fe}_2\text{O}_3}}{3\rho_{\text{MO}\cdot\text{Fe}_2\text{O}_3}} \approx 1.5 \times 10^{-5} \text{ m}^3 \cdot \text{mol}^{-1}$$

$(\text{mmol}_{\text{Fe}} \cdot \text{L}^{-1})^{-1}$


$$\frac{r_2 \times \phi_{\text{intra}}}{M_v^2} = a_{\text{theory}} \quad d^2 = 6 \times 10^{-12} \text{ } d^2$$

$$a_{\text{theory}} = \frac{2}{405} \frac{M_{\text{Fe}_2\text{O}_3}}{\rho_{\text{Fe}_2\text{O}_3}} \frac{\gamma^2 \mu_0^2}{D}$$


with $D_{\text{H}_2\text{O}} = 3 \times 10^{-9} \text{ m}^2 \cdot \text{s}^{-1}$ at 37°C




(a) USPIO
Geometrical parameters: d and ϕ_{intra}



(c) SPIO





(b) USPIO
Geometrical parameters: d and ϕ_{intra}




Building USPIOs' assemblies by “brick and mortar” concept

Poly(trimethylammonium ethylacrylate) (PTEA)



$d_H = 60 \text{ nm}$

electrostatic clusters (coacervates) with double hydrophilic block copolymers (DHBC)




Citrate, PAA_{2k}, PAA_{5k}...


Guinier's radii (giration):

$R_G = 165 \text{ \AA}$ with PTEA_{5k}-*b*-PAM_{30k}

$R_G = 188 \text{ \AA}$ with PTEA_{11k}-*b*-PAM_{30k}






Berret J-F, Schonbeck N, Gazeau F, El Kharrat D, Sandre O, Airiau M, Vacher A, JACS. (2006) **128** 5 1755;
 Berret J-F, Sehgal A, Morvan M, Sandre O, Vacher A, Airiau M, J. Coll. and Inter. Sci. (2006) **303** 315;
 Berret J-F, Sandre O, Mauger A, Langmuir (2007) **23**(6) 2993



“one-shot” mixing





Clustering of USPIOs: strong impact

T_2 Relaxometry




J-F.Berret, N. Schonbeck, F. Gazeau, D. El Kharat, O. Sandre, A. Vacher, M. Airiau, *Controlled clustering of superparamagnetic nanoparticles using block copolymers: Design of new contrast agents for magnetic resonance imaging.* JACS 2006. 128 1755

Perfectly spherical SPIO electrostatic clusters (coavervates) by controlling the desalting kinetics








Fresnais J., Berret J.-F., Qui L., Chapel J.-P., Castaing J.-C., Sandre O., Frka-Petescic B., Perzynski R., Oberdisse J., Cousin F., *Phys. Rev. E*, **78** 040401R (2008)

T₂ contrast: One master curve for all published (U)SPIOs...




Relaxivity dependence upon USPIOs' size



Vuong, Berret, Fresnais, Gossuin, Sandre, *Adv. Health. Mat.* **1**(4) 502-512 (2012)

Optimization of MRI negative T_2 contrast agents: Two curves for all published (U)SPIO(N)s !



Vuong, Berret, Fresnais, Gossuin*, Sandre*, *Adv. Health. Mat.* **1**(4) 502-512 (2012)


P. Gillis, R. Brooks, *Mag. Res. Med* **47** (2002) 257

$$r_2^* = \frac{R_2^*}{[\text{Fe}]} = \frac{2\pi\gamma\mu_0\nu_{\text{mat}}M_v}{9\sqrt{3}} \approx r_2$$

Maximum T_2 relaxivities for different types of MNPs

$$\Delta\omega = \frac{\gamma\mu_0 M_v}{3}$$

$$\tau_D = \frac{d^2}{4D}$$



$$\Delta\omega \cdot \tau_D \approx 10$$


Type of contrast agent	M_v $A \cdot m^{-1}$	$d_{optimal}$ nm	r_2^{max} $s^{-1} \cdot mM^{-1}$
Maghemite nanoparticles	3.5×10^5	55	750
Clusters of maghemite nanoparticles at a volume dilution of 5 $(\phi_{intra}=20\% v/v)$	7×10^4	120	750
Iron/iron oxide core-shell particles	6.6×10^5	38	1200
$(Zn_{0.4}Mn_{0.6})Fe_2O_4$ nanoparticles	8.75×10^5	35	1860

Vuong, Berret, Fresnais, Gossuin*, Sandre*, *Adv. Health. Mat.* 1(4) 502-512 (2012)

The scaling law fits perfectly data for $\gamma\text{Fe}_2\text{O}_3@\text{SiO}_2$ particles

"Relaxometric Studies of $\gamma\text{-Fe}_2\text{O}_3@\text{SiO}_2$ Core Shell Nanoparticles: When the Coating Matters" Sonia L. C. Pinho, Sophie Laurent, Joao Rocha, Alain Roch, Marie-Helene Delville, Stéphane Mornet, Luis D. Carlos, Luce Vander Elst, Robert N. Muller, Carlos F. G. C. Geraldes, *J. Chem. Phys.* C 116 (2012) 2285

	r_2 (20 MHz, $\text{s}^{-1} \text{mM}^{-1}$)	TEM diameter magneto metric (nm)	NMRD diameter (nm)	NMRD diameter (nm)	calculated M_{sat} of particle) ^a	calculated M_{sat} TEM (A m ² /kg of particle) ^b
FF	129.25 ± 3.88	9.6 ± 1.3	10.9 ± 0.12	13.6 ± 0.1	51.1	51.1
FF@SiO ₂ _1	114.18 ± 3.43	11.2 ± 1.7	11.3 ± 0.12	16.1 ± 0.1	39.4	40.4
FF@SiO ₂ _2	96.16 ± 2.89	24.7 ± 3.2	11.0 ± 0.12	21.8 ± 0.1	21.3	6.2
FF@SiO ₂ _3	85.89 ± 2.58	46.4 ± 8.0	11.1 ± 0.12	27.6 ± 0.2	11.9	1.00
FF@SiO ₂ _4	50.25 ± 1.51	73.8 ± 8.1	11.2 ± 0.12	38 ± 0.3	4.94	0.25
FF@SiO ₂ _5	39.78 ± 1.19	94.9 ± 7.0	11.2 ± 0.14	40 ± 0.8	4.27	0.12
FF@SiO ₂ _6	40.57 ± 1.22	114.2 ± 12.7	11.2 ± 0.12	36 ± 0.6	5.76	0.07
FF@SiO ₂ _7	39.18 ± 1.18	152.9 ± 13.1	11.1 ± 0.12	43.8 ± 0.9	3.29	0.03





Fitting of T1 NMRD profiles with the Outer Sphere model

By P. Arosio, T. Orlando, F. Orsini, and A. Lascialfari (INSTM, Milano)

using the “Outer-Sphere” model

Arosio et al, *J. Mater. Chem. B*, 2013, 1, 5317-5328




NMRD T1: $f_{\max} \approx 4$ MHz, $f_{\text{infl}} \approx 15$ MHz
 $t_D = R^2/D = 3.2 \cdot 10^{-9}$ s → $R_{\text{NMR}} = 5.57$ nm
 $D_{\text{H}_2\text{O}} = 2 \cdot 10^{-9}$ m²/s
 $r_1^{\max} \approx 9$ s⁻¹·mM⁻¹ → $m_s = 54.1$ emu/g

NMRD T1 : $f_{\max} \approx 1$ MHz, $f_{\text{infl}} \approx 4$ MHz
 $t_D = R^2/D = 1.6 \cdot 10^{-8}$ s → $R_{\text{NMR}} = 10.1$ nm
 $D_{\text{H}_2\text{O}} = 1.5 \cdot 10^{-9}$ m²/s
 $r_1^{\max} \approx 90$ s⁻¹·mM⁻¹ → $m_s = 67$ emu/g

perfect agreement with magnetometry

Use of MRI contrast to map temperature?




A. Hannecart, D. Stanicki, L. Vander Elst, R. N. Muller, S. Lecommandoux, J. Thévenot, C. Bonduelle, A. Trotier, P. Massot, S. Miraux, O. Sandre, and S. Laurent, *Nano-thermometers with thermo-sensitive polymer grafted USPIOs behaving as positive contrast agents in low-field MRI*, *Nanoscale*, [2015. 7: 3754-3767](#)

Use of (U)USPIOs for T_1 -contrast: known by radiologists

C. Corot et al. (Guerbet)

Advanced Drug Delivery Reviews 58 (2006) 1471–1504



Atherosclerotic MR-imaging in rabbits 5 days after the injection of 1000 μmol . Fe/kg of Ferumoxtran-10

Left: Normal rabbit: bright blood due to the T_1 effect of ferumoxtran-10 (AMI-227, T-10 Dextran coating)*


Right: Atherosclerotic rabbit: note the dark signal in the vessel wall due to the macrophage uptake of ferumoxtran-10 in atherosclerotic lesions.





Angio-MR in rabbit after the injection of 45 μmol Fe/kg of ferumoxtran-10 (AMI-227). Due to the blood pool effect, even small arteries and veins are visible

* 4-5 nm core, $D_H=28$ nm, $r_2/r_1=2.1$ at 20MHz (Forge et al, *Contrast Media Mol. Imaging* 2010, 5 126–132)




Use of (U)USPIOs for T_1 -contrast: chemists who know...



4 nm core size




8.3±2 nm core size



T. Borase, T. Ninjbadgar, A. Kapetanakis, S. Roche, R. O'Connor, C. Kerskens, A. Heise, D. F. Brougham, *Angew. Chem. Int.-Ed.* 2013 52, 164

U. I. Tromsdorf, O. T. Bruns, S. C. Salmen, U. Beisiegel, H. Weller, *Nano Lett.* 2009 9, 4434

Grafting of thermo-sensitive chains onto USPIOs' surface




R = H for (EO) or CH₃ for (PO)

Jeffamine® M-2005 : PEO₅-st-PPO₃₆
Jeffamine® M-2070 : PEO₄₆-st-PPO₁₃

LCST values:



Jeffamine® M-2005 :
22±1°C (DLS / NMR)

Jeffamine® M-2070 :
52±1°C (DLS / NMR)




Chemical route:

- 1/silanization
- 2/amide bond formation





A. Hannecart, M.Sc. Thesis (UMONS, 2012)

Size distribution of magnetic cores




in diethyleneglycol (170°C)





- median: $d_0=8$ nm
- standard width ($\ln d$): $\sigma=0.4$
- number-average: $d_n=8.6$ nm
- weight-average: $d_w=13.9$ nm
- polydispersity index: $D=1.6$

Forge, D.; Roch, A.; Laurent, S.; Tellez, H.; Gossuin, Y.; Renaux, F.; Vander Elst, L.; Muller, R. *N. J. Phys. Chem. C* **2008**, *112*, 19178-19185

Solution properties of the poly(ether)amine chains





Jeffamine® M-2005 : $\text{PEO}_5\text{-st-PPO}_{36}$
 Jeffamine® M-2070 : $\text{PEO}_{46}\text{-st-PPO}_{13}$



LCST values:
 Jeffamine® M-2005 :
 $22 \pm 1^\circ\text{C}$ (DLS / NMR)
 Jeffamine® M-2070 :
 $52 \pm 1^\circ\text{C}$ (DLS / NMR)

Colloidal behavior of the grafted USPIO nanoparticles



Jeffamine® M-2005 : $\text{PEO}_5\text{-st-PPO}_{36}$
 Jeffamine® M-2070 : $\text{PEO}_{46}\text{-st-PPO}_{13}$

→ electro-steric stabilization (TEPSA charges not totally screened by poly(ether) chains)

Thermo-gravimetric study of the grafted USPIOs

Sample (coating)	Bound water (wt. %)	Inorganics =Iron oxide (wt. %)	Total organics = (wt. %)	TEPSA + (wt. %)	Polymer (wt. %)
TEPSA coated	2.7 ^a	87.5 ^a	12.5 ^a	12.5 ^a	0
		100 ^b	14.3 ^b	14.3 ^b	
M-2005 coated	1.4 ^a	60.1 ^a	39.9 ^a	8.6 ^a	31.3 ^a
		100 ^b	66.4 ^b	14.3 ^b	52.1 ^b
M-2070 coated	1.6 ^a	77.8 ^a	22.2 ^a	11.1 ^a	11.1 ^a
		100 ^b	28.5 ^b	14.3 ^b	14.2 ^b

^a relatively to dry matter at 120°C; ^b ratio to burnt matter at 600°C.

$n_{\text{polymer}} \approx 430$ chains per USPIO
for Jeffamine® M-2005

($M_w^{\text{polymer}} = 2400 \text{ g} \cdot \text{mol}^{-1}$)


$n_{\text{polymer}} \approx 100$ chains
for M-2070

($M_w^{\text{polymer}} = 2800 \text{ g} \cdot \text{mol}^{-1}$)





molecules per nm² : grafting
 -TEPSA : 2.6 yield:
 - M-2005 : 1.1 43%
 - M-2070 : 0.26 10%

$$\frac{\text{organic wt.\%}}{\text{inorganic wt.\%}} = \frac{n_{\text{TEPSA}} \times M_w^{\text{TEPSA}}}{M_w^{\text{USPIO}}} + \frac{n_{\text{polymer}} \times M_w^{\text{polymer}}}{M_w^{\text{USPIO}}}$$

$$M_w^{\text{USPIO}} = \rho \times N_A \times \frac{4}{3} \pi r_{\text{USPIO}}^3$$




Fitting of the NMRD profiles by the Outer Sphere model




Relaxivities vs. temperature: at low magnetic field/freq.

r_1





8.25 MHz (0.2 T)



NP-JeffamineM2005
NP


20 MHz (0.47 T)

r_2




Relaxivities vs. temperature: at high magnetic field/freq.

r_1





60 MHz (1.4T)







300 MHz (7T)

r_2




300 MHz (7T)

From thermo-sensitive relaxivities to positive MR contrast



High-field MRI: negative contrast due to aggregation




High-field MRI
(300 MHz,
 $B_0=7.05\text{T}$)


→ the TEPSA control USPIOs remains dispersed even under strong B_0 and induces positive contrast

→ the aggregation effect above LCST is enhanced by dipolar interaction for M-2005 coated-USPIOs

$T < \text{LCST}$



$T > \text{LCST}$



Future Developments

9

144

9 Future Developments

A. Hannecart, D. Stanicki, L. Vander Elst, R. N. Muller, S. Lecommandoux, J. Thévenot, C. Bonduelle, A. Trotier, P. Massot, S. Miraux, O. Sandre, and S. Laurent, *Nano-thermometers with thermo-sensitive polymer grafted USPIOs behaving as positive contrast agents in low-field MRI*, *Nanoscale*, 2015, 7: 3754-3767

Low-field MRI is a fallow-lying field. For decades, the technical developments mainly addressed MRI with higher field strength. Very few attempts have been made, to transfer this progress to systems with a field strength below 0.5 T.

To activate our fantasy, let us have a look on possible developments specifically for low-field MRI systems.

9.1 Technical Improvements

9.1.1 Magnet Design

There have been a lot of innovative designs. Toshiba developed the OPART, a 0.35 T system with a high-temperature superconducting magnet.

The four poles of the magnet enabled wide open access at a high mechanic stability. This system is no longer available.

The C-arm concept is most frequently used for permanent magnet systems. Mainly Hitachi and Siemens pursue this design (Fig. 9.1).

A variation of the C-arm concept is a tiltable magnet, realized by Esaote. The G-scan magnet can be tilted, to enable weight-bearing examinations, which are of importance in musculoskeletal imaging (Fig. 9.2).

Another innovative approach has been proposed by FONAR, with one magnet on the ceiling and one on the ground, resulting in a 360° open magnet. The MRI is installed as work in progress in Oxford/GB (Fig. 9.3).

The FONAR Upright MRI is an open 0.6 T system with a resistive electromagnet for functional imaging. It fills a small, but important market segment (Fig. 9.4). PARAMED Inc./Italy has combined an upright imaging concept with tiltable table/seat, providing new application options.

A very innovative approach is the development of single-sided MRI. It is used for the so-called magnetic particle imaging (MPI). In MRI, the influence of tissue substance on the relaxation properties of protons is measured. In MPI, the



Fig. 9.1 Open C-arm Magnets: Left Siemens Magnetom C! 0.35 T. Right: Hitachi Aperto 0.4 T



Fig. 9.2 Esaote G-scan Brio with a field strength of 0.25 T

magnetization of the magnetic particles (magnetites, ultrasmall particles of iron oxide USPIO) is measured directly.


This method can produce extremely high-resolved images in low magnetic fields (0.164 T) using the T1 relaxation time shortening. A vertical resolution of up to 20 µm is possible (Rössler et al. 2014). The magnetite particles are thermosensitive and can be used as nanothermometers, behaving as positive contrast agents in low-field MRI (Hannecart et al. 2015) (Fig. 9.5).

These different magnet designs give an impression of the variability of applications. Innovative magnet design is facilitated by low-field concepts.


High-field MRI: prevent aggregation in Matrigel™

SEM image of Matrigel™ (10 mg/mL BD Sci.) from R. Poincloux et al, *Journal of Cell Science* 122, 3015-3024

- dense protein network of meshsize 50-500 nm
- Viscous liquid at 4°C
- Gel at 37°C




Ferro@Jeffamine B₀=4.7T (200MHz)



High-field MRI
(200 MHz, $B_0=4.7\text{T}$)


r_2/r_1 remains limited (aggregation prevented)
but both relaxivities are significantly decreased, maybe due
to water confinement effect like in USPIO up-taken by cells
Cf. Ribot et al, *Contrast Media Mol. Imaging* 2009, 4 109–117

Magnetic Responsive Polymer Composite Materials



J. Thévenot, H. Oliveira, O. Sandre, S. Lecomandoux, **Chem. Soc. Rev.** [2013, 42, 7099-7116](#)

Magnetic Responsive Polymer Composite Materials



J. Thévenot, H. Oliveira, O. Sandre, S. Lecomandoux, **Chem. Soc. Rev.** [2013, 42, 7099-7116](#)

Thermotherapies as old as Hippocrates !

10

M.H. Seegenschmidt and C.C. Vernon

**Diese punchlein saget
uns von allen padem
die von natur heiss seint**



which dates back to about 3000 b.c. (BREASTED 1930). Therein a clinical report is presented of a woman suffering from a (malignant?) breast tumor. In this case it was recommended that the tumor be treated by means of the so-called fire drill, which was clearly meant to be a local caustic therapy. Subsequently, such local **heat** treatments were described in numerous other reports by Greek and Roman physicians. This ancient confidence in the application of local **heat** is underscored by one of the famous aphorisms of the Greek physician **Hippocrates**, who stated (translated in Latin words, according to OVERGAARD 1985):

*Quae medicamenta non sanant, ferum sanat.
Quae ferum non sanat, ignis sanat.
Quae vero ignis non sanat, insanabilia reportari oportet.*

which means:

Those who cannot be cured by medicine can be cured by surgery.
Those who cannot be cured by surgery can be cured by **heat**.
Those who cannot be cured by **heat** are to be considered incurable.

1st attempt of magnetic hyperthermia by physicians (not physicists!)


R. K. Gilchrist, R. Medal, W. D. Shorey, R. C. Hanselman, J. C. Parrot, 2386 and C. B. Taylor, *J. Ann. Surg.* 146, 596 (1957).

A broad variety range of MFH applicators

- Lab-made setups
 - Commercial setups for other purposes than MFH research (dentistry, jewelry, soldering)
 - Commercial setups dedicated to MFH research
-
- Applicators for SAR measurements
 - Applicators for in vitro MFH (Petri dishes for cell culture)
 - Applicators for in vivo MFH (pre-clinical assays on rodents, clinical assays on humans)
-
- Mono-frequency solid-state generators *vs.* multi-frequencies resonant circuits
 - Open coils *vs.* ferrite circuits: control of field lines
 - Hollow pipe *vs.* multi-strand conductor (Liz wire), water-circulation *vs.* air-cooling...
-
- Adiabatic conditions or not (need thermal loss correction)
 - Thermometry: localized T-measurement (fiber probe) *vs.* infrared thermometry
 - H field intensity and frequency assessment: redaction of a technical note by WG4

General concepts

a) Coil vs. b) Ferrite core



From E. Garaio-Urabayen PhD Thesis, UPV-EHU, March 2015

$$B(\text{Tesla}) \approx \frac{\mu_0 N \times I}{L}$$


- a) Air-coils sample located in the center where the H field is more homogeneous and intense
 - b) Ferrite cores to concentrate the magnetic flux B inside sample, more homogeneous field
- When large usable-gaps or usable volumes are required (whole human body applicators), electromagnetic applicator based on ferromagnetic cores are preferred). However, ferrite cores implies additional power consumption, especially at high frequencies.

In vivo applicator: clinical (human)

Clinical human applicator

Pr Andreas Jordan, Charité hosp. Berlin

MagForce AG, www.magforce.de



NanoPlan®:
Computer-assisted
Injection of magnetic
NPs in glioblastoma



NanoTherm®: 15nm
cores, -NH₂ coated

$$C_{\gamma-\text{Fe}_2\text{O}_3}^{\text{tumor}} \approx 160 \text{ g/L}$$

2003: Beginning of phase 1 clinical trial

2007: End of phase 1 clinical trial

2011: End of phase 2 clinical trial (68 patients)


Nowadays: Authorized on market in Europe



NanoActivator®

$$T_{\text{tumor}} = 43-50^\circ\text{C}$$

$$f_{\text{RF}} = 100 \text{ kHz}, H_{\text{max}} = 2 - 18 \text{ kA/m}, B_{\text{max}} = 2.5 - 23 \text{ mT}$$



Picture of prototype (courtesy L. Vekas)

Components Of The NanoTherm® Therapy: *Novel method for local treatment of tumors*

THERAPY PLAN

1. INJECTION



Iron oxide nanoparticles are injected directly into the tumor using conventional methods following therapy planning

NanoTherm® is a colloidal dispersion of superparamagnetic iron oxide nanoparticles with a diameter of approx. 15 nm and a coating of aminosilane. The iron concentration of the dispersion is 112 mg/ml (or 335 mg/ml)

NanoTherm® is injected directly into the tumor in an intraoperative procedure

Due to their special coating, the nanoparticles remain at the injection site

2. TUMOR TEMPERATURE SIMULATION



Treatment temperatures and corresponding magnetic field strengths are defined by the physician before the start of therapy (Post Implantation Analysis, PIA)

The software NanoPlan® simulates temperature distribution in the treatment area and suggests magnetic field strength for NanoTherm® therapy

The basis of the treatment plan is the concentration and position of the nanoparticles in the tumor measured by postoperative CT and temperature maxima defined by the physician

Components Of The NanoTherm® Therapy:


AN ALTERNATING MAGNETIC FIELD, WHICH CHANGES ITS POLARITY 100,000 TIMES PER SECOND, ACTIVATES THE NANOPARTICLES

- Magnetic field activates Neel and Brownian relaxation processes of iron oxide nanoparticles generating heat
- Magnetic field strengths of approx. 2-15 kA/m
- NanoActivator™ induces therapeutic treatment temperatures within the tumor of > 40 °. Thermotherapy effect enhances the efficacy of radio- and chemotherapy
- Innovation values of NanoActivator™
- Can be applied to solid tumors in all body regions
- First therapy device specifically for nanomedicine
- Dose adjustment during therapy by regulating the magnetic field strength
- Direct intratumoral temperature measurement during therapy for securing optimal therapeutic temperatures and patient safety



In vivo applicators: pre-clinical (rodents)



Example of lab-made in vivo setup



Nanotherics magneTherm™

Heat-Generating Iron Oxide Nanocubes: Subtle “Destructurators” of the Tumoral Microenvironment

Direct injection of nanocubes in the tumor (0.7 mg iron)




Ovarian tumors A431 cells

Exposure to the alternating magnetic field (3x 30 min)

control



110 kHz – 23,8 kA/m




J. Kolosnjaj-Tabi et al
ACS Nano 8, 4268, 2014

Nanotherics magneTherm™

Recommended accessory for *in vivo* experiments:
Mouse restrainer / water-jacket (37°C)







2 coils Helmholtz-like configuration



Rodrigues, Bakuzis, to appear in *Physics in Medicine and Biology* (IOP journal)

DM3 from nanoScale biomagnetics



Applicators for SAR measurement

Example of lab-made SAR measurement setup (Paris 97')



Current generator : 300 kHz at $f = 1.1 \text{ MHz}$ / $I_{\max} = 12 \text{ A}$

J. Servais, MSC – Univ. Paris 7

J-P. Fortin et al

JACS 129, 9, 2628-2635, 2007

Fiber optic thermometer




Thermal regulation (circulation of C_9H_{20} instead of water)


Coil: $\emptyset 12 \text{ mm} / H=1.8 \text{ (kA}\cdot\text{m}^{-1}\text{)}/\text{A}$ ($H_{\max}=21.6 \text{ kA}\cdot\text{m}^{-1}$)

Measurement of magnetic hyperthermia efficiency

Measurements of the heat generation by ultra-small superparamagnetic iron oxide particles (USPIO) under AC magnetic field by calorimetry (here: non-adiabatic condition)
 → Specific Absorption Rate (SAR) or Specific Loss Power (SLP)



$$f_{RF} = 755 \text{ kHz}, H_{\max} = 10.2 \text{ kA/m}$$



'stepped heating' N. Iacob et al, *Eur. Phys. J. E* (2015) 38: 57


4.18J needed to heat 1g of water by 1°C

→ convert slopes $\Delta T/\Delta t$ into SAR values in W/g (of iron oxide)

Experimental conditions of 120 publications over 25 years compared to 'Brezovich criterion' $H_0 \cdot f < 4.8 \times 10^8 \text{ A(ms)}^{-1}$

Scatter size proportional to $H_0 \cdot f$ product

SAR measurement
in vivo
in vitro
in vivo & in vivo



Fundamentals and advances in magnetic hyperthermia,

E. A. Périgo, G. Hemery, O. Sandre, D. Ortega, E. Garaio, F. Plazaola, F. J. Teran
 Applied Physics Reviews 2, 041302 (2015)

Bordeaux-Bilbao collaboration on magnetic hyperthermia



- **University of Basque Country (Bilbao, Spain)**

Team of Fernando Plazaola (Vice-Rector), Eneko Garaio, Jose-Angel Garcia (Phys.), Juan-Mari Collantes (Electr. Eng.), MD Javier Echevarria

eman ta zabal zazu



UPV EHU

- **Université de Bordeaux / CNRS**

Team of Sébastien Lecommandoux, Olivier Sandre (LCPO)

Team of Etienne Duguet, Stéphane Mornet, Graziella Goglio (ICMCB)

Team of Franck Couillaud (RMSB), MD Nicolas Grenier, MD Hugues Loiseau, MD Arnaud Hocquelet

Setups travelling between Bilbao and Bordeaux



LCPO' "magnethermon" brought to Bilbao by Hugo Oliveira for *in vitro* expts at CIC biogune (Edurne Berra) in July 2012 European NMP-Health-FP7"



Leader: Gaiker (Bilbao) www.nanother.eu
dedicated to cancer nanotherapy (11 M€)

In Bordeaux: LCPO, RMSB, CBMN



In Bilbao and San Sebastian: CIC biogune, Gaiker, Vicomtech




Bilbao's setup (Eneko Garaio's prototype)
brought to Bordeaux for SAR measurements in
Spring 2014



Example of lab-made setup: all Bilbao's setups




Bordeaux's setup improved with help of UPV-EHU




Thermal Dose & Power Control by Eneko Garaio




"VASCO Flex" by Cordouan Technologies
(startup company nearby Bordeaux campus)





Aquitaine



LCPO/2011/159




Calorimetry vs. magnetometry to measure SAR




Eneko Garaio-Urabayen PhD Thesis 2015, UPV-EHU, Bilbao

- E. Garaio, J. M. Collantes, J. A. García, F. Plazaola; S. Mornet, F. Couillaud, and O. Sandre, *A wide-frequency range AC magnetometer to measure the specific absorption rate in nanoparticles for magnetic hyperthermia*. **J. Mag. Mag. Materials**, [2014. 368: 432-437](#)
- E. Garaio, O. Sandre, J-M. Collantes, J. A. Garcia, S. Mornet, and F. Plazaola, *Specific absorption rate dependence on temperature in magnetic field hyperthermia measured by dynamic hysteresis losses (AC Magnetometry)*, **Nanotechnology**, [2015. 26: 015704](#)
- E. Garaio, J-M. Collantes, J. A. Garcia, F. Plazaola, and O. Sandre, *Harmonic phases of the nanoparticle magnetization: an intrinsic temperature probe*, **Applied Physics Letters**, [2015. 107: 123103](#)
- E. A. Périgo, G. Hemery, O. Sandre, D. Ortega, E. Garaio, F. Plazaola, and F. J. Teran, *Fundamentals and advances in magnetic hyperthermia*, **Applied Physics Reviews**, accepted, [arXiv:1510.06383](#)



The heating efficiency (SAR) varies with temperature




$d_{TEM} = 12.9 \pm 4.6 \text{ nm}$ for sample III




$d_{TEM} = 16.9 \pm 1.7 \text{ nm}$ for sample IV



(c) Sample III




(d) Sample IV




- E. Garaio, O. Sandre, J-M. Collantes, J. A. Garcia, S. Mornet, and F. Plazaola, *Specific absorption rate dependence on temperature in magnetic field hyperthermia measured by dynamic hysteresis losses (AC Magnetometry)*, *Nanotechnology*, 2015. **26**: 015704

The forced hydrolysis route or “New Orleans synthesis”

D. Caruntu, G. Caruntu, Y. Chen, C. J. O'Connor, G. Goloverda,
V. L. Kolesnichenko, *Chem. Mater.* **2004**, *16*, 5527-5534



Poly(hydroxy) amine/Polyol viz. N-methyl diethanolamine /
DEG (1:1)








- 6 mmol FeCl₂
- 12 mmol FeCl₃
- 180g DEG
- 180g NMEDA
- 220°C 5h

Reflux
Stirring shaft

Internal T-probe

Aspiration flask for
washing steps

Ferrite slab for magnetic
sedimentation




- 2nd heat/stirrer for
precursor dissolution
Dry heating mantle
(up to 250°C)


- Precursor
- Polyol composition
- Temp/Duration
- Water content

Variety of Fe_3O_4 NP batches synthesized in DEG:NMDEA


$$\langle d \rangle = d_0 e^{\sigma^2/2} \quad var(d) = d_0^2 (e^{\sigma^2/2} - 1)$$




4FF: $d=6.2\pm1.0$ nm




23FF: $d=10.5\pm1.9$ nm




25FF: $d=14.2\pm3.2$ nm



29FF: $d_{out}=26.6\pm4.2$ nm





15FF: $d_{out}=36.3\pm4.8$ nm






30FF: $d_{out}=41.1\pm8.6$ nm

Utmost importance of controlling water addition





Chosen nanoflower sample: FF15






- Can be oxidized in boiling $\text{Fe}(\text{NO}_3)_3$: $\text{Fe}_3\text{O}_4 \rightarrow \gamma\text{-Fe}_2\text{O}_3$
- Washed and stabilized in water at $\text{pH} \sim 7$ with citrate ligand

DC magnetization curves of FF15 nanoflowers



Peculiar Spin-Glass Dynamics of Nanoflowers




A. Kostopoulou, K. Brintakis, M. Vasilakaki, K. N. Trohidou, A. P. Douvalis, A. Lascialfari, L. Manna, A. Lappas, *Nanoscale* 6, 3764 (2014)






Different spin-dynamics / relaxation times τ
 Interplay of dipolar interactions with spin disorder
 due to the defected surface coordination (PAA)
 → memory effects in the high T_B

AC hysteresis curves of FF15 nanoflowers

1.7 mg/mL Fe_3O_4





1.0 mg/mL $\gamma\text{-Fe}_2\text{O}_3$



Measurements done by Eneko Garaio (UPV-EHU Bilbao)

SPM-FM transition depends on applied frequency!




1. High f : $\text{SAR} \sim H_{\text{app}}^2$ scaling consistent with SPM state
(Néel relaxation main contribution to heating)
2. Low f : weak SAR below threshold field ($H_{\text{max}} < H_{\text{aniso}}$)
and scaling exponent $>>2$ for $H_{\text{max}} > H_{\text{aniso}}$ followed by plateau
→ so-called “Stoner-Wohlfarth behavior” by J. Carrey & G. Goya

Measurements done by Eneko Garaio (UPV-EHU Bilbao)

Modeling mag. moment dynamics by Fokker-Planck equation

Two-region modelling of nanoflower:



→ Total diameter 45 nm and volume fractions:



$$\varphi_{Core} = \left(\frac{d_{Core}}{d_{core} + 2d_{surface}} \right)^3 \approx 0.17$$

$$\varphi_{Surface} = 1 - \varphi_{Core} \approx 0.83$$

$$M_{total} = \varphi_{surface} M_{surface} + \varphi_{core} M_{core}$$





Calculated hysteresis:

Maghemite:
 $M_{spe} = 300 \text{ kA/m}$
 $K_{eff} = 8 \text{ kJ/m}^3$




Simulation done by Eneko Garaio (UPV-EHU Bilbao)

The phase of $M(H)$ harmonics enables measuring T !



- E. Garaio, J-M. Collantes, J. A. Garcia, F. Plazaola, and O. Sandre, *Harmonic phases of the nanoparticle magnetization: an intrinsic temperature probe*, *Applied Physics Letters*, [2015. 107: 123103](#)

Magnetic hyperthermia works at macroscopic scale (tumor Ø~1cm), but what about the cellular or micro-metastasis level (Ø~10-100µm)?




La magnéothermocytolyse

H. Halbreich, F. Gazeau

LMDH (univ P6, P7) 1997


$$\frac{1}{r^2} \frac{\partial}{\partial r} \left(k_w r^2 \frac{\partial T}{\partial r} \right) + P = \rho C_p \frac{\partial T}{\partial t} \rightarrow \Delta T = \frac{P}{k_w R} \propto R^2$$



$$\Delta T_{local} \approx 6^\circ\text{C}$$

Y. Rabin: Is intracellular hyperthermia superior to extracellular hyperthermia in the thermal sense?
Int. J. Hyperthermia 2002 18, 194-202.

Cellular hyperthermia is still a very hot debate!



CORRESPONDENCE

$$\Delta T_{\max} = SAR \cdot C_{\gamma Fe_2O_3}^{\text{drop}} \cdot \frac{4\pi r^2}{k_{\text{medium}}}$$

and the complexity of the membrane structures in intracellular organelles could contribute to the uneven temperature distribution. The complex and highly organized structure of the cells also strongly affects heat capacity c and may further elicit emergent behaviors (frequently described as “the whole is greater than the sum of the parts”), which disallow a simple adoption of equation (2), in subcellular heat diffusion. Therefore, we believe one must carefully consider this fact before employing equation (1) based upon steady-state and uniformity to interpret thermal properties of a real cell.

Additionally, we believe that the underlying assumption guaranteeing the validity of the macroscopic equation (2) may not hold for the actual conditions inside cells. Equation (2) assumes that the local equilibrium is preserved at every ‘point’ (in a macroscopic sense) in the surrounding medium under consideration, and therefore the point should correspond to a real volume of the order of $1 \mu\text{m}^3$, according to ref. 8 (we interpret this reference to state that the threshold of applicability is true not only for the gas phase but also for liquid and solid phases). We also interpret ref. 8 to state that the size L of the heat source must be much larger than $1 \mu\text{m}$ for this equation to be applicable. Fluctuations of thermodynamic quantities will be significant and will violate the prerequisite homogeneity in small ($<1 \mu\text{m}$) systems, whereas they become completely immaterial at a larger length scale. The actual sizes of the heat sources, namely protein complexes and intracellular organelles, are $10-100 \text{ nm}$ in size. Additionally, several heat sources exist in cells in a discontinuous manner. Therefore, we believe that it is necessary to adopt a heat diffusion equation with additional parameters.

We note that the active ion transport and the accompanying heat transport in Ca^{2+} -ATPase, or a temperature difference between the cytosol and endoplasmic reticulum (ER) and the corresponding heat flux across ER lumen, have been simulated by using the theory of mesoscopic nonequilibrium thermodynamics^{10,11}. A similar approach may help interpret cellular thermal changes. We believe that equation (2) with appropriate values of κ and c is still valid for a nonuniform system such as a cell if the system may be properly represented by a coarse-grained continuum characterized simply by κ and c .

Furthermore, our experimental observations using tsGFP1-mito or tsGFP1-ER, targeted to the mitochondria or ER, respectively, clearly revealed the temperature changes in HeLa cells, brown adipocytes and differentiated myotubes, in contrast to tsGFP1 expressed throughout the cytosol³. This difference between tsGFP constructs supports the view that the generated heat was transferred directly to organelle-targeted tsGFP1s in the same compartment, for compartment sizes less than 100 nm , but reached the cytosolic tsGFP1 only after being diffused. This also might be the case in the observed higher temperature of the nucleus compared with the cytosol using fluorescent polymeric thermometers within the same compartment². Inhibiting various biochemical processes in the nucleus should confirm this finding. We believe it will be critical to assess the effects of different subcellular environments through precise evaluation of the fluorescence properties of targeted thermosensors.

Validating subcellular thermal changes revealed by fluorescent thermosensors

To the Editor: In their recent Commentary arguing that a single cell cannot substantially raise its temperature by endogenous thermogenesis, Baffou *et al.* raised a critical issue¹ concerning the observations of temperature rise of ΔT in single cells and of subcellular thermal heterogeneities^{2,3}. They argue that the observed ΔT (1–2 K) of a whole cell^{2,3} would be much larger than the theoretical ΔT estimated from the relation

$$\Delta T = \frac{P}{\kappa L} \quad (1)$$

where κ is conductivity, L is the diameter of the heat source and P is power.

This is derived from the macroscopic heat diffusion equation for continua

$$c \partial_r T(r, t) - \kappa \nabla^2 T(r, t) = p(r, t) \quad (2)$$

where c is volumetric heat capacity and $T(r, t)$ and $p(r, t)$ are temperature and heat source density as a function of position r and time t .

We believe that the issue requires a deeper examination regarding the values of the parameters used in the calculation of ΔT from the relation (1) and the validity of the basic equation (2) for cellular systems.

Baffou *et al.* estimated ΔT within a cell to be around 10^{-5} K , assuming that the heat source size is $10 \mu\text{m}$ and that the average heat production per hour based on glucose production is 100 pW (360 nJ h^{-1}). Considering the transience and localization of actual heat production within intracellular organelles, they further estimated the energy required to increase 1 K over a $1-\mu\text{m}^3$ volume during 1 s to be $1 \mu\text{J}$, which is still one or two orders of magnitude higher than the maximum energy produced by the total glucose contained within a cell¹. In their estimation, they adopted $\kappa = 1 \text{ W m}^{-1} \text{ K}^{-1}$, representing a watery environment, for the medium surrounding the heat source. However, the interior of a cell is far different from a watery environment. For example, proteins, water and lipids all possess different κ values (0.6 and $0.1-0.2 \text{ W m}^{-1} \text{ K}^{-1}$ for water and proteins, respectively⁵). In addition, the typical size of the heat source in mitochondria is less than 100 nm .

Taking $L = 100 \text{ nm}$ and $\kappa = 0.1 \text{ W m}^{-1} \text{ K}^{-1}$ to reflect the high concentration of the intracellular proteins, we reestimate the heat required for an increase of 1 K over the volume of the heat source within mitochondria ($10^{-3} \mu\text{m}^3$) during 1 s to be 10 nJ , in contrast to the $1 \mu\text{J}$ calculated by Baffou *et al.* Notably, our value agrees well with the heat production of $3-5 \text{ nJ s}^{-1}$ in brown adipocytes obtained using microcalorimetry^{6,7}. We also note that the heterogeneity in the conductivity of intracellular components

CORRESPONDENCE

COMPETING FINANCIAL INTERESTS

The authors declare no competing financial interests.

Shigeki Kiyonaka^{1,2}, Reiko Sakaguchi³, Itaru Hamachi¹, Takashi Mori⁴, Takenao Yoshizaki⁵ & Yasuo Mori^{1,2}

¹Department of Synthetic Chemistry and Biological Chemistry, Graduate School of Engineering, Kyoto University, Kyoto, Japan. ²Department of Technology and Ecology, Hall of Global Environmental Studies, Kyoto University, Kyoto, Japan.

³World Premier International Research Initiative-Institute for Integrated Cell-Material Sciences, Kyoto University, Kyoto, Japan. ⁴Institute of Advanced Energy, Kyoto University, Kyoto, Japan.

⁵Department of Polymer Chemistry, Graduate School of Engineering, Kyoto University, Kyoto, Japan.

e-mail: mori@sbchem.kyoto-u.ac.jp

1. Baffou, G., Rignault, H., Marguet, D. & Jullien, L. *Nat. Methods* **11**, 899–901 (2014).
2. Okabe, K. *et al.* *Nat. Commun.* **3**, 705 (2012).
3. Kiyonaka, S. *et al.* *Nat. Methods* **10**, 1232–1238 (2013).
4. Sakaguchi, R., Kiyonaka, S. & Mori, Y. *Curr. Opin. Biotechnol.* **31**, 57–64 (2015).
5. Lervik, A., Bresme, F., Kjelstrup, S., Bedeaux, D. & Rubi, J.M. *Phys. Chem. Chem. Phys.* **12**, 1610–1617 (2010).
6. Clark, D.G., Brinkman, M. & Nevile, S.D. *Biochem. J.* **235**, 337–342 (1986).
7. Hansen, E.S. & Knudsen, J. *Biosci. Rep.* **6**, 31–38 (1986).
8. Kondepudi, D. & Prigogine, I. in *Modern Thermodynamics: From Heat Engines to Dissipative Structures* 333–350 (Wiley, 1998).
9. Bedeaux, D. & Kjelstrup, S. *Phys. Chem. Chem. Phys.* **10**, 7304–7317 (2008).
10. Lervik, A., Bedeaux, D. & Kjelstrup, S. *Eur. Biophys. J.* **42**, 321–331 (2013).

the center of the heat source, L (units in meters) (Supplementary Discussion), and is as follows:

$$\Delta T = \frac{P}{\kappa L}$$

where ΔT represents the temperature difference (in kelvin), P represents the power of the heat source (in watts) and κ represents the thermal conductivity of the medium surrounding the heat source ($\text{W m}^{-1} \text{ K}^{-1}$). Yang *et al.*² argued that the deviation of measured ΔT originated from the distribution of L . In accordance with this idea, we detected no notable distribution in ΔT when our molecular thermometers targeted the endoplasmic reticulum (zero distance)—which is considered the major heat source in calcium shock measurements—without distribution of L (ref. 6 and Supplementary Discussion).

Second, Baffou *et al.* concluded that it is unlikely that the temperature of water with volume of $1 \mu\text{m}^3$ can be sustained at 1 K higher than the surrounding medium for longer than a few seconds by means of the oxidation of stored glucose. However, most thermosensors used in intracellular thermometry are smaller than $1 \mu\text{m}^3$ by two or more orders of magnitude (Supplementary Discussion). Also, Baffou *et al.* appear to have ignored glucose uptake in stimulated cells (Supplementary Discussion). Furthermore, their argument relies on general well-established equilibrium thermodynamics (historically developed for large steam engines) that do not take into consideration the realistic boundary conditions of heat transfer at the micro- or nanoscale in a cell. Thus, we believe that their argument does not necessarily invalidate the reported transient temperature dynamics.

Baffou *et al.*'s third point is that a single lipid bilayer is deficient in the thermal resistivity needed to result in a higher temperature value in an organelle than in cytosol¹. Again, temperature discontinuity was calculated by assuming bulk-type heat flow. But we believe that this does not match the reality of the complex intracellular structure of a cell (Supplementary Discussion).

Finally, we agree with Baffou *et al.* that it is important to test the robustness of intracellular thermosensors with respect to environmental parameters other than temperature changes. Environmental impacts (inhomogeneous in space and time) need to be controlled in order to make progress in temperature imaging in single cells. Most studies cited by Baffou *et al.* have noted the utmost importance of deciphering potential sources of error in measurements (Supplementary Table 1). We therefore do not believe that all the data measured by means of completely different kinds of thermosensors can be attributed to factors other than temperature changes.


We expect that once the aforementioned uncertainties of variable heat sources in stimulated cells (10^4), length scales (10^1-10^2), and micro- and nanoscale thermal parameters ($10^{-10}-10^2$) are clarified, the 10^5 gap issue may disappear. We envisage that these unknowns will be the next targets for investigation in this field.

Note: Any Supplementary Information and Source Data files are available in the online version of the paper (doi:10.1038/nmeth.3551).

ACKNOWLEDGMENTS

The authors acknowledge support from a Grant-in-Aid for Scientific Research on Innovative Areas (no. 2306) and Scientific Research (C) (to M.S.), Young Scientist (A) (to K.O.) and Specially Promoted Research and Scientific Research (S) (to S.I.) from the Ministry of Education, Culture, Sports, Science and Technology of Japan.

Detection of hyperthermia in micro droplets $R=200\mu\text{m}/V=33\text{nL}$




$Q_{\text{oil}} (\mu\text{L/mn})$	$Q_{\text{FF}} (\mu\text{L/mn})$	$t_{\text{residence}} (\text{s})$	$\Phi_{\text{FF}} = Q_{\text{FF}}/Q_{\text{tot}}$
90	15	85	14.3%
150	15	54	9.1%
150	50	45	25%

D. Habault et al, *IEEE Transactions on Magnetism* (2013)

49 182-190, DOI: 10.1109/TMAG.2012.2221688




In situ measurement of the train of drops temperature




The dominant phenomenon is thermal conduction towards medium, here a fluorinated oil (C_6F_{14}) with $k_{oil} \sim k_{water}/10$

Varying power at constant $Q_{FF}=20\% Q_{total}$





ΔT (K)


ΔT (K) vs. $\ln(H_0^2)$





Varying MNP flowrate (% of total flowrate)



Detection of *in vivo* effects of magnetic hyperthermia: droplets Ø~1mm of fluorinated MF on mice skin




Analysis of bioluminescence vs.
deposited thermal dose



LCPO Laboratoire de Chimie
des Polymères Organiques
Genes [2017 8, 61](#)

In vitro and in vivo studies on tumor models to determine ΔT_{max} reachable after intra-tumor vs. intravenous injection of MNPs


- *In vitro:* magnetic bio-gels in a mouse model (agar gel)




Undergoing experiments with S. Mornet (ICMcb), P. Durand and F. Couillaud (RMSB)

- *In vivo:* magnetic bio-gels injected subcutaneously


100 μ L magnetic Matrigel™ placed in fat layer (3 mm thick) below skin (1 mm) and above muscles and blood (2 mL). Power density=1 W/cm³. Tumor phantom heated at 45°C at center and 42°C in periphery.



New commercial *in vivo* MFH setup (*nB* DM3)




- 146 kHz, 27.6 mT
- 217 kHz, 26 mT
- 344 kHz, 20.4 mT
- 473 kHz, 16.8 mT



Mission interdisciplinarité
Centre national de la recherche scientifique



“défi nano 2014”



RF induction heating for magnetic drug release (magneto-chemotherapy): more gentle process than pure hyperthermia

Thermoresponsive polymer brush-functionalized magnetic manganite nanoparticles for remotely triggered drug release


S. Louguet.. S. Mornet, E. Duguet, S. Lecommandoux, C. Schatz
Polym. Chem., 2012, **3**, 1408




C. Sanson, O. Diou, O. Sandre, S. Lecommandoux, *ACS Nano* 2011, **5** 1122

BBA - General Subjects 2017

[doi: 10.1016/j.bbagen.2017.02.025](https://doi.org/10.1016/j.bbagen.2017.02.025)



Liu et al, *Nanoscale*
2013, 5, 11464




Setup for model drug release experiment through drug diffusion across semi-permeable membrane

- 1: Solenoid and calculated magnetic field lines
 - 2: Dialysis bag (e.g. Spectra/Por Float-A-Lyzer™, 50000 g·mol⁻¹ MWCO, 10 mm diameter, 5 mL volume)
 - 3: Cylinder (50 mL) filled with aqueous buffer
- Usually the drug is titrated in the outer medium, in "sink" and thermostatic (37°C) conditions.

Preparation method of nanosized polymersomes from a rigid ($T < T_g$) or semi-crystalline ($T < T_m$) amphiphilic copolymer

Nanoprecipitation, e.g. PS-
b-PEO, PLA-*b*-PEO,
PCL-*b*-PEO...



Vs. Direct dissolution (DD)
for low T_g blocks: PBA-*b*-PAA, PBD-*b*-PEO, PDMS-*g*-PEO, PEO-*b*-PDMS-*b*-PEO ...
(in buffered solution at 50 °C)

self-assembly mechanism called “nanoprecipitation” or “solvent displacement”*

Solvated chains

ill-defined aggregates

Micelles

Block copolymer self-assembly

constant N_{agg}

Good solvent
(organic)

Nucleation

Vesicle

Growth

Intra-aggregate rearrangements

Selective solvent
(water)


Critical water fraction
End of unimers diffusion

Sanson et al, Langmuir 26
(2010) 2751

*Johnson et al. Phys. Rev. Lett. 2003
Lince et al. J. Coll.& Interf. Sci. 2008

Co-assembly in polymersomes for dual-loading

Self-assembly by “solvent displacement” method (nanoprecipitation)




* LD₅₀ by iv: 2.5-11g/kg (cats, dogs, monkeys, rabbits, mice, rats...)

Sanson et al. *Langmuir* **26**, 2751 (2010); *ACS Nano* **5**, 1122 (2011)

Magnetic micelles and vesicles self-assembled from MNPs and amphiphile diblock “rod-coil” copolymers

Poly(ethylene oxide)-block-poly(γ -benzyl-L-glutamate)




PEG-*b*-PBLG

- Bioresorbable
- Stealth properties

- Bioresorbable
- Synthetic polyaminoacid
- Rigid hydrophobic block
- Rod-like (helical) structure


Poly(trimethylene carbonate)-block-poly(L-glutamic acid)



PTMC-*b*-PGA


- Bioresorbable
- Semi-crystalline for $M_n < 12\,000$ g/mol : **Melting at $T_m \approx 37^\circ C$**

- Synthetic polyaminoacid
- Bioresorbable
- pH responsive
→ 2ndary structure transition



Sanson et al. *Langmuir* **26**, 2751 (2010); *Soft Matter* **6**, 1722 (2010); *J. Contr. Rel.* **147**, 428 (2010); *ACS Nano* **5**, 1122 (2011)

Micelles




$$2R_G = 0.775D_H$$



$$\Phi_{\text{intra}} = N_{/\text{object}}^{\text{USPIO}} \left(\frac{2R_G}{D_{\text{USPIO}}} \right)^3$$

P. Arosio et al. *J. Mater. Chem. B*
2013, **1**, 5317-5328

Vesicles




Magnetic polymer vesicles: structural study




TEM

C. Sanson et al *ACS Nano* 5, 1122 (2011)

CryoTEM




A. Brisson, CBMN




*Magnetic guiding of PTMC-*b*-PGA vesicles under *B* gradient*

Optical video microscopy under magnetic field gradient




Magnetic guiding of PTMC-*b*-PGA vesicles under *B* gradient



SPIONs particles for all bio-related properties: MRI, tumor homing & hyperthermia / magnetic drug release

T₂ relaxivity



Magnetophoretic mobility

$$r_2 \Phi_{\text{intra}} = \frac{R_2}{[\text{Fe}]} = \frac{2}{405} \frac{M_{\text{Fe}_2\text{O}_3}}{\rho_{\text{Fe}_2\text{O}_3}} \frac{\gamma^2 \mu_0^2 M_v^2 d^2}{D}$$

$$M_v = \Phi_{\text{intra}} M_{\text{spe}}$$

at high field: $B_0 > 0.94\text{T}$
($> 40\text{MHz}$)

$$\vec{F}_v = 3\pi \eta d \vec{v}$$

$$\vec{F}_m = \mu_0 \chi \vec{\nabla}_z (\frac{1}{2} H_0^2) \frac{\pi}{6} d^3$$

$$\chi = \frac{\mu_0 \pi}{18k_B T} \Phi_{\text{intra}} M_{\text{spe}}^2 d_{\text{core}}^3$$

at low field: $B_0 < 0.1\text{T}$
but high field gradient: $\nabla B_0 = 10-100\text{T/m}$

$$r_2 = 11.6 \times 10^{-12} \Phi_{\text{intra}} M_{\text{spe}}^2 d^2$$


$$\frac{v_{\text{mag}}}{\vec{\nabla}_z (\frac{1}{2} B_0^2)} = \frac{\pi d_{\text{core}}^3}{(18)^2 \eta k_B T} \Phi_{\text{intra}} M_{\text{spe}}^2 d^2$$

For a given batch of USPIOs (M_{spe} and distribution of d_{core} sizes), the design of clusters of controlled geometry (Φ_{intra} and d) enables to tune both MRI contrast and guiding properties

Both parameters (r_2 and v_{mag}) can be measured by MRI, as in A. Ionescu et al. *Nanotechnology* 19 (2008) 395102:
 $d_{\text{core}} = 9.6\text{nm}$, $d = 12\mu\text{m}$, $\Phi_{\text{intra}} = 0.6$, $M_{\text{spe}} = 2.35 \times 10^5 \text{A/m}$, $\eta = 10^{-3}\text{Pas}$, $T_2^* = 50\mu\text{s}$, $[\text{Fe}] = 48\text{g/L} \equiv 600\text{mM} \rightarrow r_2 = 33\text{s}^{-1}/\text{mM}_{\text{Fe}}$, $B_0 = 7\text{T}$, $\nabla B_0 = 1.21\text{T/m}$, $v_{\text{mag}} = 5 \times 10^{-4}\text{m/s}$

Magnetic vesicles as negative MRI contrast agents

Relaxation rates ($r_2 = 1/T_2$) versus iron concentration



Vesicles with 70 wt % SPIO at different dilution factors

$[Fe]$ (μM)	H_2O	21	37	49	74	148
$[\text{copo}]$ ($\mu\text{g/mL}$)	H_2O	2.9	5	6.7	10	20

MR detection limit: copolymer concentration at which the MRI signal intensity decreases to 50 % of that of pure water


➡ 0.6 nM vesicle concentration

For comparison, threshold for **PCL-*b*-PEG** micelles loaded with **16 nm Fe_3O_4 NPs**
 → 5 nM (*Gao et coll. Adv. Mat. 2005*)

Wt % SPIO	r_2 ($\text{Fe} \cdot \text{mM}^{-1} \cdot \text{s}^{-1}$)
20	85
35	141
50	177
70	178


➡ **r_2 increases with SPIO loading content**

➡ **Good T2 contrast agent for MRI**




C. Sanson et al, *ACS Nano* 5, 1122 (2011)

Collaboration with RMSB:
 Line Pourtau, Sylvain Miraux, Eric Thiaudière





L. Pourtau, H. Oliveira, J. Thévenot, Y. Wan, A. Brisson, O. Sandre, S. Miraux, E. Thiaudière, and S. Lecommandoux, *Advanced Healthcare Materials*, 2013, 2, 1420–1424


In vitro tumor targeting efficacy



Cell internalization by FACS



Breast cancer cell lines:



Overexpress HER2
(Human Epidermal Growth Factor Receptor-2)

Internalization ↗ by targeting in
HER2 positive cells



In vitro tumor targeting efficacy

Cell internalization by MRI

24h incubation time
0.2 mg/mL particles





Cells embedded into a gel and
imaged by MRI




→ Both methods (FACS and MRI) confirm the specific internalization of antibody-bearing polymersomes in HER2 positive cells

L. Pourtau, H. Oliveira, J. Thévenot, Y. Wan, A. Brisson, O. Sandre, S. Miraux, E. Thiaudière, S. Lecommandoux, *Advanced Healthcare Materials*, 2013, 2, 1420–1424


A



B



Real time 3D MR imaging at 4.7 T of the distribution of hybrid polymersomes after *iv* injection of a 100 μL bolus of contrast agent at a dose of 250 $\mu\text{mol Fe/kg}$ (15 mg/mL copolymer) injected in the mouse tail vein.




Dual loaded polymers with the anthracycline anticancer drug doxorubicin (up to 30 wt%) and USPIOs (up to 70 wt%)


Doxorubicin-loaded PTMC-*b*-PGA polymersomes

- ❖ Incorporation during the nanoprecipitation process (DOX in DMSO)
- ❖ Optimal loading with carbonate buffer pH 10.5


PTMC₂₄-*b*-PGA₁₅
+ 6-7nm γ-Fe₂O₃ USPIOs



Loading content (LC) up to 70 wt% (12 vol%) USPIOs without size change



hematological cancers, carcinoma, sarcomas...
free drug or as liposomal formulation (Doxil™)




PTMC₂₄-*b*-PGA₁₅
+ 50 wt% 6-7nm USPIOs
+ DOX



wt _{dox} /wt _{copo} (%)	D _h Contin(nm)	PDI	Zeta (mV)
0	113	0.22	-40.8
20	122	0.15	-42
30	274	0.20	NA

RF induction heating for drug release (magnetochemotherapy): latest assays “in cellulo” (magneto-cytotoxicity)

H. Oliveira et al, J. Contr. Rel. 2013 169(3), 165-170



Vesicles loaded at $6 \pm 1\%$ doxorubicin, size: 192 nm (pdi=0.1)





Thank you for your attention

o CNRS-MI

Mission interdisciplinarité
Centre national de la recherche scientifique

“défi nano” (2012, 2014-2015)

o Cancéropôle GSO

**Cancéropôle**
Grand Sud-Ouest

Bordeaux ● Limoges ● Montpellier ● Nîmes ● Toulouse

o C’Nano GSO

**NanoSciences**
GRAND SUD - OUEST



o Agence Nationale de la Recherche
“MagnetoChemoBlast” (2013-2017)

AGENCE NATIONALE DE LA RECHERCHE
ANR


“Multifunctional Nanoparticles for Magnetic Hyperthermia and Indirect Radiation Therapy”

o National Science Foundation
France/Belgium iREU in Translational Chemistry
Louis Stokes Alliances for Minority Participation



o Europe
<http://cost-radiomag.eu/>

**COST**
EUROPEAN COOPERATION IN SCIENCE AND TECHNOLOGY
TD1402 - RADIOMAG



21 countries



Roadmap:

- Better design of nanoparticles for *in vivo* hyperthermia
- Standardize SAR measurement
- *In vivo* assays: pre-clinical and towards clinical trials
- Temperature mapping (intra-tumoural)